



GOLI VODIČI (Cu)



BARE CONDUCTORS (Cu)



Cu VODIČ		
SIROVINA	Bakar (Cu)	čistoća 99,99%
NORMA	ASTM EN	B 49 1977
PROIZVODNE DIMENZIJE	Maksimalni odnos $b_1 : s_1$	10 : 1
	Minimalni presjek (mm^2)	10
	Maksimalni presjek (mm^2)	150
PROIZVODNE DIMENZIJE	Okrugla žica	$\geq 0,300-3,000\text{mm}$
NORMA	IEC	60317-0-2 60317-0-1
VODLJIVOST	kod 20°C	$\geq 58 \text{ MS/m}$
SPECIFIČNI OTPOR	kod 20°C	$\leq 0,017 \Omega\text{mm}^2/\text{m}$

Cu CONDUCTOR		
RAW MATERIAL	Copper (Cu)	Purity 99,99%
NORM	ASTM EN	B 49 1977
PRODUCTION DIMENSIONS	Max. Ratio $b_1 : s_1$	10 : 1
	Min. Cross Section (mm^2)	10
	Max. Cross Section (mm^2)	150
PRODUCTION DIMENSIONS	Round wire	$\geq 0,300-3,000\text{mm}$
NORM	IEC	60317-0-2 60317-0-1
CONDUCTIVITY	at 20°C	$\geq 58 \text{ MS/m}$
SPECIFIC RESISTANCE	at 20°C	$\leq 0,017 \Omega\text{mm}^2/\text{m}$